



Technical data for Gibo Plast A/S PC

CAS nr.: 25037-45-0

Listed data is the minimum requirements for the all products in that specific kategori, PC, PC UVP and RPC, unless marked with (Max).
Data with a tolerance is marked by(±X%). All products are extruded.

GENERAL

Property	Method	Unit	PC	PC UVP	RPC
Density (±3%)	ISO 1183	g/cm ³	1.2	1.2	1.2
Water absorption (Max)	DIN EN ISO 62 Method 1	%	0.20	0.15	-
Ball indentation hardness	ISO 2039-1	MPa	100	130	130

MECHANICAL

Property	Method	Unit	PC	PC UVP	RPC
Tensile strength	ISO 527-2	MPa	50	60	60
Elongation at break	ISO 527-2	%	80	80	50
Tensile modulus	ISO 527-2	MPa	2200	2200	2300
Flexural strength	ISO 178	MPa	95	95	90
Flexural modulus	ISO 178	MPa	2200	2300	2300
Impact strength @23 °C (Charpy unnotched)	ISO 179-1	KJ/m ²	No break	No break	No break
Impact strength @23 °C (Charpy notched)	ISO 179-1	KJ/m ²	10	10	10

THERMAL

Property	Method	Unit	PC	PC UVP	RPC
Vicat temperature (B 50) (±1%)	ISO 306	°C	146	146	-
Service temperature (Continuous use)	-	°C	100	115	115
Max. temperature (Short term use)	-	°C	125	130	120

OPTICAL

Property	Method	Unit	PC	PC UVP	RPC
Light transmission	DIN 5036-3/ EN ISO 13468-2	%	86	86	-

Gibo Plast A/S | Ferrodanvej 14 | DK-6900 Skjern | Tlf: +45 8782 8700 | Fax: +45 8725 1110 | E-mail: post@giboplast.com

The technical data have been collected and categorised by Gibo Plast A/S in good faith. They are non-binding and do not represent a material specification or assurance of specific properties. We explicit reserve the right to change or update these instructions at any time.

Further processing and use of the products can have various impact on the products. Therefore, Gibo Plast A/S, does not guarantee or warrant for the fitness, suitability or adequacy of the products for any purpose intended by the purchaser or any third person and shall have no liability whatsoever in this respect. The purchaser has the obligation to test the products and determine itself is the products are fit for the intended use.

Gibo Plast A/S shall neither nor indirectly, indemnify and hold harmless purchaser or any third person in the event of any third-party claims related to the infringement of intellectual property rights.